NOTES:

1. ALL EDGES SHALL BE FREE OF BURRS.
2. FINISH 125 EXCEPT AS NOTED.
3. TEST: UNDER A STATIC LOAD OF 60 LBS THE LOSS IN FREE HEIGHT, AFTER RECOVERY, SHALL NOT EXCEED .010.
4. DIM -A- APPLIES AFTER SPRING HAS BEEN COMPRESSED FLAT AND ALLOWED TO SPRING BACK FREE ONE TIME.
5. HEAT TREATMENT: HEAT TO 1450°-1500° F. OIL QUENCH. TEMPER 30 MINUTES AT APPROXIMATELY 700° F. HEAT TREATMENT METHOD IS FOR GUIDANCE EXCEPT THAT TEMPERING TIME SHALL NOT BE REDUCED BELOW THAT SPECIFIED. NO DECARBURIZATION PERMISSIBLE.
6. FINAL PROTECTIVE FINISH: FINISH 5.3.1.2 OR 5.3.2.2 OF MIL-STD-171 (DO NOT GRIT BLAST)
7. MIL-W-13855 SHALL APPLY



C7312732

P	NOR G2S3011/92-02-04	92 0303	
N	(ECPW5S2069 /851223 NORW4S2051/840824	860121	
M	NOR W6S2022/79-03-26	79-04-01	SAC
L	SEE ERR HQR 40681	10 FEB 75	
K	SEE EO HRD 02136	21 FEB 69	
J	(1) SEE EO HRD 92078-2	25 JUN 68	
H	SEE EO 82048	11 MAR 68	
G	(1) SEE EO SA 29261	18 MAY 66	
F	SEE EO SA 27608	7 SEP 65	
E	SEE EO SA 27501	7 AUG 64	
D	SEE EO SA 26980	21 AUG 63	
C	REDRAWN AND REVISED SEE EO SA24529	10 JUL 58	
B		1 DEC 54	
STR	DESCRIPTION	DATE	APPROVAL

REVISIONS

CURRENT DESIGN ACTIVITY FSCM NO. 19200
U.S. ARMY ARMAMENT RESEARCH AND DEVELOPMENT CENTER
DOVER, NEW JERSEY 07801

PART NO. 7312732

PHYSICAL PROPERTIES	
YP	
TS	
EL 2	
RA	
BH	
BH	SUPERFICIAL 30N 83-85

D11010363	RIFLE M14NM
A11010364	RIFLE, M14 30R-MI MIC & MID

NEXT ASSY | USED ON
APPLICATION
DO NOT APPLY PART NO.

TOLERANCES ON DECIMALS ANGL FRACTIONS
MATERIAL STEEL, ASTM A684, 1095 SPHEROIDIZED ANNEALED
HEAT TREATMENT SEE NOTE 5
FINAL PROTECTIVE FINISH SEE NOTE 6

ORIGINAL DATE OF DRAWING 9 DEC 44
DRAFTSMAN E.R.C. CHECKER
TRACER CHECKER
ENGINEER R.S. Henry DRAWER
SUBMITTED R.S. Henry ORD CORPS
APPROVED

SPRING, REAR SIGHT
CAGE CODE 19205

SPRINGFIELD ARMORY SPRINGFIELD, MA.

DWG SIZE C | 7312732
SHEET 1 OF 1

RMH